


de HAVILLAND

CAGE CODE 71867
CV STANDARD



MAT'L AL ALLOY 7150-T61511
AMS 4307

UNLESS OTHERWISE STATED FED. STD #245 TOLERANCES APPLY
MIN. LENGTH 35 FT.

NOTES:

- 1) FULL SECTION TENSILE TEST SPECIMENS SHALL BE TAKEN FROM THE REAR END OF THE EXTRUDED LENGTH.
- 2) **PROFILE SHOWN MUST NOT CONTAIN ANY INTERGRANULAR CORROSION.** ADDITIONAL MATERIAL MAY BE ADDED ALL AROUND, TO BASIC EXTRUSION, AND THEN MACHINED OR CHEM-MILLED TO OBTAIN THE FINAL DIMENSIONS SHOWN.
- 3) SPECIAL TOLERANCES ARE MARKED WITH AN ASTERISK (*).
- 4) THE EXTRUSION SHALL BE MARKED WITH THE CV # EVERY 3 FEET. **MARKING METHOD SHALL NOT HAVE A DETRIMENTAL EFFECT ON THE MATERIAL.**
- 5) CV 726 HAS THE SAME PROFILE, DIMENSIONS, TOLERANCES, AND ALLOY, BUT CALLS OUT A DIFFERENT TEMPER.
- 6) ☒ 125 MAX. FOR CHEM-MILLED SURFACES.

FOR ORIGINAL SIGNATURES, AND THE RESPONSIBLE DESIGNER, SEE THE ENGINEERING STANDARDS APPROVAL RECORD

DESIGNED	H. Sabeti-Mehr	EXTRUDED 'J' SECTION	CV 804
STRESS	E. Berzonis		
MAT. TECH	E. Levy		
STDS REL	S. Schrattnner		
		DATE: 1996.03.02	REVISION: A

THE INFORMATION, TECHNICAL DATA AND DESIGNS DISCLOSED IN THIS DOCUMENT (THE "INFORMATION") ARE EITHER THE EXCLUSIVE PROPERTY OF DE HAVILLAND INC., OR ARE SUBJECT TO PROPRIETARY RIGHTS OF OTHERS. THE INFORMATION IS NOT TO BE USED FOR DESIGN OR MANUFACTURE, OR DISCLOSED TO OTHERS WITHOUT THE EXPRESS PRIOR WRITTEN CONSENT OF DE HAVILLAND INC. THE HOLDER OF THIS DOCUMENT, BY ITS RETENTION AND USE, AGREES TO HOLD THE INFORMATION IN CONFIDENCE. THESE RESTRICTIONS DO NOT APPLY TO PERSONS HAVING PROPRIETARY RIGHTS IN THE INFORMATION, TO THE EXTENT OF THOSE RIGHTS.