

de HAVILLAND

CAGE CODE 71867

DSC STANDARD

	DSC565-1			
Distributor	see Note 1			
Product Ident	Loctite 409			
Colour	Clear			
Gap Fill	.010"			
Resin Base	Ethyl			
Viscosity cP	Gel			
Tensile Strength (psi)	3,200			
Temperature Range	-65° F to 180° F			
Cure Speed Fixture Full	75 sec. 24 hrs.			
Specific Gravity	1.10			
Ordering Information	3 gm tube 10 gm syringe 20 gm tube/bottle 200 gm tube 300 gm cartridge			
Acceptance Testing & Re-Life Testing	Refer to Quality Assurance Material Testing Requirement (QAMTR 017)			

NOTES:

1. Loctite Canada, Mississauga, ON

SEE ENGINEERING STANDARDS APPROVAL RECORD FOR ORIGINAL SIGNATURES AND CHANGE SUMMARY

DRAWN	P. LAM	ADHESIVE, GENERAL PURPOSE	DSC 565
CHECKED	S. GIRI		
STRESSED	A. BOTTUSSI		SHEET: 1 of 1
APPROVED	S. CACOUTIS		

REV:

REV:

REV:

REV:

REV:

REV:

APPROVED: 07 MAR 2002