



THE INFORMATION, TECHNICAL DATA AND DESIGNS DISCLOSED IN THIS DOCUMENT (THE "INFORMATION") ARE EITHER THE EXCLUSIVE PROPERTY OF BOMBARDIER INC., OR ARE SUBJECT TO PROPRIETARY RIGHTS OF OTHERS. THE INFORMATION IS NOT TO BE USED FOR DESIGN OR MANUFACTURE, OR DISCLOSED TO OTHERS WITHOUT THE EXPRESS PRIOR WRITTEN CONSENT OF BOMBARDIER INC. THE HOLDER OF THIS DOCUMENT, BY ITS RETENTION AND USE, AGREES TO HOLD THE INFORMATION IN CONFIDENCE. THESE RESTRICTIONS DO NOT APPLY TO PERSONS HAVING PROPRIETARY RIGHTS IN THE INFORMATION, TO THE EXTENT OF THOSE RIGHTS.

**de HAVILLAND**

**CAGE CODE 71867  
DSC STANDARD**

**SOURCE CONTROL DRAWING**

ONLY THE ITEM(S) LISTED ON THIS DRAWING AND IDENTIFIED BY VENDOR'S NAME(S), ADDRESS(ES) AND PART NUMBER(S) HAVE BEEN APPROVED FOR USE IN DE HAVILLAND AIRCRAFT. A SUBSTITUTE ITEM SHALL NOT BE USED WITHOUT PRIOR APPROVAL BY DE HAVILLAND ENGINEERING STANDARDS



Top Sandwich Panel View

**SKIN:** 2 PLIES OF .008" - .010" THICK FIBERGLASS (CDM010-02 TYPE I, GRADE B), WARP 90°

**ADHESIVE:** NIL (SELF ADHESIVE SKIN)

**CORE:** NOMEX HONEYCOMB, 1/8" CELL, 4.0 LB/CU FT (CDM020-01 TYPE 3, GRADE A), RIBBON 90°

DASH NO.	t THICKNESS (inch) ± .010	VENDOR PART NO.	LONG BEAM BENDING L-DIRECTION (RIBBON) ASTM C393, MIN. VALUE (in-lb/in)	PEEL STRENGTH W-DIRECTION (TRANSVERSE RIBBON) ASTM D1781, MIN. VALUE (in-lb/3in width)	WEIGHT MAX. (lb/sq ft)
-1	.50	CDM200-92-4-10	202 @ 10" support span mid-point load	20	.57

**SUPPLIER:** JD LINCOLN INC., COSTA MESA, CA, USA 92627

**SIZE:** 48" X 96" (TOLERANCE ± .50")

SEE ENGINEERING STANDARDS APPROVAL RECORD FOR ORIGINAL SIGNATURES AND CHANGE SUMMARY

DRAWN	J. MacCOLL	<b>PANEL, NORTHWEST COMPOSITES</b>	<b>DSC 575</b>
CHECKED	B. EDWARDS		
STRESSED	F. LAU		SHEET: 1 of 2
APPROVED	D. PECILE		

REV:

REV:

REV:

REV:

REV:

REV:

APPROVED: 24 AUG 2004

**NOTES:**

1. FLAMMABILITY REQUIREMENT:

FAR 25.853 Appendix F, Part I(a)1(i) - (60 sec.vertical)

2. PROCESS CONTROL DOCUMENT:

CDP500-00 REV 'H'

3. Values per table above and flammability adherence must be demonstrated on a lot (batch) basis. Test one panel per lot made. Test panel must be made from the same lot (batch) of core, prepreg (if applicable), adhesive etc. Any changes in the above lot (batch) will constitute a new panel lot, and will require a new test panel.

4. Vendor shall issue a Certificate of Compliance along with a Test Report for each shipset.

**NOTE:**

**THE SUPPLIER SHALL WORK TO THE REVISION LEVEL OF THE REFERENCED DOCUMENTATION ONLY.**

**THE SUPPLIER SHALL ADVISE BOMBARDIER AEROSPACE - de HAVILLAND IN ADVANCE OF ANY CHANGE OR REVISION TO REFERENCED DOCUMENTS CONTAINED IN THIS DSC THAT WOULD RESULT IN REQUALIFICATION/ RECERTIFICATION.**

SEE ENGINEERING STANDARDS APPROVAL RECORD FOR ORIGINAL SIGNATURES AND CHANGE SUMMARY

DRAWN	J. MacCOLL	<b>PANEL, NORTHWEST COMPOSITES</b>	<b>DSC 575</b>
CHECKED	B. EDWARDS		
STRESSED	F. LAU		SHEET: 2 of 2
APPROVED	D. PECILE		