

As of August 30, 2016, the following PPS's have been released, having been revised as noted below:

PPS 31.02, Issue 34 - Cleaning Processes for Aluminum and Aluminum Alloys

- Specified that de-ionized water rinse temperature shall be 60 to 90°F in place of 208 to 212°F in Table I, Solution Make-Up.
- Processing before sulphuric acid anodizing (A3), specified final de-ionized water rinse temperature to be 60 to 90°F in place of 65 to 85°F.
- For panels used for end grain pitting and intergranular attack, specified panel size to be 1 inch width, 2 inch length by 0.125 to 0.250 inch thick.

This revision notice lists brief summaries of technical changes introduced for each of the revised PPS's. Please note that these summaries are not detailed and are intended only to assist in alerting PPS users to changes which may affect them; refer to the applicable PPS for authorized, detailed procedure and requirements.
